



[Rubber stamp]

---

# P A T E N T

---

## UTILITY CERTIFICATE – CERTIFICATE OF ADDITION

---

### OFFICIAL COPY

The Director-General of the Institut National de la Propriété Industrielle certifies that the attached document is a true copy of an application for industrial property titleright filed at the Institute.

Drawn up in Paris, 25 NOV. 2004

On behalf of the Director-General of the  
Institut National de la Propriété Industrielle  
The Patent Department Head

[signature]

[Stamp: **PRIORITY  
DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1 (a) OR (b)]

Martine PLANCHE

---

INSTITUT 26 bis, rue de Saint Petersburg  
NATIONAL DE 75000 PARIS Cédex 08  
LA PROPRIÉTÉ Telephone: 33 (0)1 53 04 53 04  
INDUSTRIELLE Fax: 33 (0)1 53 04 45 23  
www.inpi.fr



26 bis, rue de Saint Pétersbourg  
75800 Paris Cedex 08  
Telephone: 33 (1) 53 04 53 04 Fax: 33 (1) 42 94 86 54

**PATENT**  
**UTILITY CERTIFICATE**  
Intellectual Property Code - Book VI

**cerfa**  
N° 11354°03

**BR1**

**REQUEST FOR GRANT**

page 1/2

Reserved for the INPI

This form is to be filled in legibly in black ink

DB 540 @ W / 210502

SUBMISSION OF DOCUMENTS

DATE **5 NOV. 2003**

PLACE **75 INPI PARIS**

NATIONAL REGISTRATION No. **03/12,973**

ASSIGNED BY THE INPI

DATE OF FILING ASSIGNED BY THE INPI **-5 NOV. 2003**

**Your file references:**

(optional) **PaC3 2003096FR**

**1** NAME AND ADDRESS OF THE APPLICANT OR THE REPRESENTATIVE  
TO WHOM THE CORRESPONDENCE IS TO BE ADDRESSED

SAINT-GOBAIN RECHERCHE  
39, quai Lucien Lefranc  
F-93300 AUBERVILLIERS  
FRANCE

**Confirmation of filing by fax**

☐ No. assigned by the INPI to the fax

**2** NATURE OF THE APPLICATION

Tick one of the 4 following boxes

Patent application

☒

Utility certificate application

☐

Divisional application

☐

*Initial patent application*

No.

Date  /  /

*or initial utility certificate application*

No.

Date  /  /

Conversion of a European patent  
application *Initial application*

☐

No.

Date  /  /

**3** TITLE OF THE INVENTION (200 characters or spaces maximum)

SIZING COMPOSITION FOR AN INSULATION PRODUCT BASED ON MINERAL WOOL, AND RESULTING PRODUCTS.

**4** PRIORITY DECLARATION OR  
APPLICATION FOR THE BENEFIT OF  
THE FILING DATE OF A PRIOR  
FRENCH APPLICATION

Country or organisation

Date  /  /

No.

Country or organisation

Date  /  /

No.

Country or organisation

Date  /  /

No.

☐ If there are other priorities, tick the box and use the "continuation" form

**5** APPLICANT (Tick one of the 2 boxes)

☒ Legal entity

☐ Natural person

Name  
or company name

SAINT-GOBAIN ISOVER

Forenames

Legal form

SIREN No.

APE-NAF Code

Domicile  
or  
registered  
office

Street

18 Avenue d'Alsace

Postcode and town

92400 COURBEVOIE

Country

FRANCE

Nationality

FRENCH

Telephone No. (optional)

Fax No. (optional)

E-mail address (optional)

☐ If there are other applicants, tick the box and use the "continuation" form

# PATENT UTILITY CERTIFICATE

REQUEST FOR GRANT

BR2

page 2/2

Reserved for the INPI

SUBMISSION OF DOCUMENTS

DATE 5 NOV. 2003

PLACE 75 INPI PARIS

NATIONAL REGISTRATION No.

03/12,973

ASSIGNED BY THE INPI

DB 540 @ W / 210502

## 6 REPRESENTATIVE (if applicable)

Name

SAINT-GOBAIN RECHERCHE

Forename

Firm or Company

No. of permanent power of attorney  
and/or contractual arrangement

422-5/S.006

Address

Street

39, quai Lucien Lefranc

Postcode and town

93300 AUBERVILLIERS

Country

FRANCE

Telephone No. (optional)

33 1 48 39 59 51

Fax No. (optional)

33 1 48 34 66 96

E-mail address (optional)

## 7 INVENTOR (S)

The inventors must be natural persons

The inventors are the applicants

☐ Yes

☒ No In this case, fill in the Designation of inventor(s) form

## 8 SEARCH REPORT

For a patent application only (including division and conversion)

Immediate compilation  
or deferred compilation

☒
☐

Fee paid in instalments  
(in two instalments)

Only for natural persons filing their own application

☐ Yes

☐ No

## 9 REDUCTION OF FEES

For natural persons only

☐ Requested for the first time for this invention (attach notice on non-application)

☐ Obtained prior to filing for this invention (attach copy of the decision granting free assistance or indicate its reference): AG

## 10 NUCLEOTIDE AND/OR AMINO ACID SEQUENCE

☐ Tick the box if the description contains a sequence listing

The computer readable form is enclosed

☐

The statement that the information recorded  
in computer readable form is identical to the  
written sequence listing is enclosed

☐

If you used the "continuation" form,  
give the number of attached pages

## 11 SIGNATURE OF THE APPLICANT OR REPRESENTATIVE

(name and capacity of the signatory)

SAINT-GOBAIN RECHERCHE

Power of Attorney No. 422-5/S.006

Patricia CHOSSON

[signature]

SIGNED FOR THE PREFECTURE  
OR THE INPI

[illegible signature]

**SIZING COMPOSITION FOR AN INSULATION PRODUCT BASED ON  
MINERAL WOOL, AND RESULTING PRODUCTS**

5 The present invention relates to the manufacture of  
insulation products, especially thermal and/or acoustic  
insulation products, based on mineral wool. More  
precisely, it relates to an improved sizing composition  
based on an epoxy resin allowing the mechanical  
strength of such products after ageing, especially in a  
10 wet environment, to be increased.

Insulation products based on mineral wool, especially  
glass or rock wool, generally take the form of  
relatively rigid panels, shelves, wound felts or even  
15 veils. They are intended in particular for the thermal  
and/or acoustic insulation of buildings.

The manufacture of such products comprises a first step  
of manufacturing the wool itself, especially using the  
20 technique known as centrifugal attenuation, in which  
the molten mineral material is converted into  
filaments, and a forming step in which the filaments  
are attenuated and entrained towards a receiving member  
by a high-temperature high-speed gas stream in order to  
25 form a sheet thereon. In order to ensure cohesion of  
the sheet, a sizing composition, which contains a  
thermosetting resin, is sprayed onto the wool as it  
travels towards the receiving member. The sheet thus  
treated is then subjected to a heat treatment in an  
30 oven in order to cure the resin and obtain a product  
having the desired properties, such as dimensional  
stability, tensile strength, tear resistance, puncture  
resistance, thickness recovery after compression, and  
homogeneous colour.

35

In the insulation product, the binder has the function  
of binding the fibres together - it must adhere  
correctly to the glass and spread uniformly over the

fibres so as thereafter to be preferably at the junction points between the fibres and thus allow a resilient fibrous sheet to be obtained.

- 5 The sizing composition is therefore preferably sprayed when the fibres are still separate fibres, that is to say before formation of the sheet. Consequently, the size is sprayed in the fibre-receiving hopper, beneath the burners that generate the attenuating gas stream.
- 
- 10 This therefore precludes the use of inflammable organic solvents and/or contaminants for formulating the size, the risk of a fire and/or of contamination in the receiving hopper being too high.
- 15 In addition, the resin serving as binder, although it must not cure too rapidly before sheet formation, it must also not have too long a cure time. By controlling this time, the risks of pregelling are thus avoided and the cure time remains compatible with high production
- 20 rates, especially by taking measures to ensure that the binder has completely cured after the high-temperature oven treatment (around 260°C).

The most commonly used sizes contain a thermosetting

25 resin of the resol type, obtained by condensation of a phenol with a formaldehyde, or equivalents, in the presence of a basic accelerator, water as dilution agent, urea, serving to reduce the amount of free formaldehyde and also acting as binder, and various

30 additives, such as aqueous ammonia, oil, coupling agents, for coupling to the glass, colorants and, optionally, fillers.

Although this type of size does allow a high level of

35 mechanical performance to be achieved, its use, especially during the oven treatment, generates undesirable gaseous emissions, for example of formaldehyde, ammonia and other volatile organic

compounds.

To alleviate this drawback, sizing compositions have been proposed that are based on an epoxy resin of the glycidyl ether type and a non-volatile amine hardener (see EP-A-0 369 848 and FR 02/08873). This solution makes it possible for the emissions to be very substantially reduced, both during manufacture of the insulation product, since complete cure can be achieved at a lower temperature (around 220°C), and during its use at high temperatures, above 150°C and up to 700°C.

Although it is important for the mechanical properties of the insulation product to be satisfactory after manufacture and up till its use, in order to ensure that it is properly installed on the site, it is also desirable for them to be maintained for a certain time once the product is in place, in order to guarantee that it has a sufficient lifetime.

For the most part, insulation products have to be subjected, as they age, to thermal cycles of relatively large amplitude and variable condensation conditions that results in them being exposed to moisture, which entails a loss of their mechanical properties. Such losses may be large when the mineral wool is particularly water-sensitive, for example when it is a wool that can dissolve in a physiological medium.

The object of the invention is to remedy these drawbacks and to improve the mechanical strength after ageing, especially in a wet environment, of insulation products based on mineral wool provided with an epoxy binder, that is to say to reduce the losses in mechanical properties of these products after ageing, especially in a wet environment.

This object is achieved according to the invention by

means of a sizing composition based on an epoxy resin of the glycidyl ether type and an amine hardener, this composition being characterized in that it furthermore includes an accelerator chosen from imidazoles,  
5 imidazolines and mixtures thereof.

The term "accelerator" here has the usual meaning in the field of chemistry and denotes a compound that increases the rate of reaction between the epoxy resin  
10 and the amine hardener.

The size makes it possible for the losses in properties after ageing, particularly wet ageing, to be markedly reduced compared with a similar product not containing  
15 the accelerator, without significantly modifying these properties just after manufacture.

Another subject of the invention is a process for manufacturing an insulation product employing the  
20 aforementioned sizing composition.

A further subject of the invention is the insulation products coated with the said sizing composition.

25 The epoxy resin according to the invention is obtained by the reaction of epichlorohydrin with an alcohol. Preferably, the alcohol is a polyol comprising at least two hydroxyl functional groups per molecule and at most 100, preferably at most 50 and better still at most 10  
30 hydroxyl functional groups per molecule. Particularly preferably, the alcohol is a diol.

Advantageously, the resin has an EEW (Epoxy Equivalent Weight) corresponding to the mass of resin, in grams,  
35 containing one gram-equivalent of epoxide functional groups, which is between 150 and 2000, preferably between 160 and 700 and better still at most equal to 300. Such a resin has the advantage of generating a

small amount of undesirable emissions during the fibrizing operation and the subsequent oven treatment, and it also remains compatible with the known processes for spraying the size onto the fibres for the purpose  
5 of forming insulation products.

Also advantageously, the resin has a functionality (number of epoxide groups per molecule) of at least 2 and preferably less than 10.

10

The epoxy resin according to the invention is water-dispersible or capable of being emulsified in the presence of an emulsifying agent or a dispersing agent. This is because it is essential for the resin to have  
15 at least one of these properties so that the sizing composition can be sprayed properly. In this regard, sprayability is dependent on the water dilutability of the resin, defined as follows: the water dilutability of an epoxy resin emulsion or dispersion is the volume  
20 of deionized water that can be added, at a given temperature, to unit volume of this composition before the emulsion or dispersion "breaks", that is to say before the said emulsion or dispersion becomes destabilized or has undergone phase separation. The  
25 water dilutability of a resin that can be used in a sprayable sizing composition is advantageously at least 500%, preferably 1000%, at 20°C.

Preferably, the epoxy resin is chosen from resins  
30 resulting from the reaction between epichlorohydrin and bisphenol A, bisphenol F, polyethylene glycols, glycerol, pentaerythritol and novolac resins, and mixtures of these resins. The resins formed by a reaction between epichlorohydrin and bisphenol A are  
35 particularly preferred.

As examples of such resins, mention may be made of:

- resins in aqueous emulsion, sold by Resolution



under the names Epi-Rez<sup>®</sup> 5003-w-55 (EEW = 195-215),  
Epi-Rez<sup>®</sup> 3510-w-60 (EEW = 185-215), Epi-Rez<sup>®</sup> 3515-w-60  
(EEW = 225-275), and Epi-Rez<sup>®</sup> 3522-w-60 (EEW = 615-715;

5       - resins that can be emulsified in water, sold by  
Resolution under the names Epikote<sup>®</sup> 828 (EEW = 184-  
190), and Epikote<sup>®</sup> 255 (EEW = 193-205) or by Dow  
Chemical under the names DER 330 (EEW = 176-185) and  
DER 331 (EEW = 182-192).

10   Other epoxy compounds of the glycidyl ether type may be  
added to the sizing composition. As examples, mention  
may be made of epoxidized aliphatic compounds and  
epoxidized fatty alcohols, useful especially for  
modifying the viscosity of the size, and epoxy resins  
15   of the halogenated glycidyl ether type, especially  
derivatives of dibromophenyl glycidyl ethers, such as  
dibromophenyl glycidyl ether, 2-methyl-4,6-dibromo-  
phenyl glycidyl ether, 4-methyl-2,6-dibromophenyl  
glycidyl ether and 4-cumyl-2,6-dibromophenyl glycidyl  
20   ether, which make it possible in particular to give the  
product better high-temperature resistance. The content  
of these compounds generally represents less than 30%,  
preferably less than 10%, by weight of the epoxy resin.

25   The amine hardener according to the invention is  
generally chosen from aliphatic polyamines, such as  
diethylenetriamine (DETA), triethylenetetramine (TETA),  
tetraethylenepentamine (TEPA) and polyglycoldiamines,  
cycloaliphatic polyamines, such as  
30   1,3-bis(aminomethyl)cyclohexane, 4,4-diaminocyclohexyl-  
methane, methylenediamine and 2,4-diaminocyclohexanol,  
and aromatic polyamines, such as m-phenylenediamine,  
m-xylylenediamine, diethyltoluenediamine, diamino-  
diphenylsulphone and dicyandiamine.

35

The amount of amine hardener to be introduced into the  
sizing composition depends on the number of amine  
reactive sites carried by the molecule. Preferably, the

hardener has an amine equivalent weight/H ratio defined as the ratio of the amine molecular weight to the number of active hydrogen atoms, which is between 20 and 300. Preferably, the amount of hardener is  
5 introduced in stoichiometric amount relative to the resin so as to avoid an excess of hardener which may lead to the emission of volatile products on the fibre-receiving belt and/or in the oven.

10 Also preferably, the hardener is non-volatile, that is to say that, under the spraying conditions, it cannot undergo spontaneous ignition. The flashpoint of the hardener is advantageously above 150°C and better still above 180°C.

15 The sizing composition furthermore includes an accelerator chosen from imidazoles, imidazolines and mixtures thereof. Choosing the accelerator from within a limited family of compounds makes it possible to  
20 achieve the performance in terms of ageing resistance, especially in a wet environment.

As examples of imidazoles, mention may be made of imidazole, 1-methylimidazole, 2-methylimidazole,  
25 2-phenylimidazole, 2-ethyl-4-methylimidazole and 4,4'-methylenebis(2-ethyl-5-methylimidazole).

As an example of an imidazoline, mention may be made of 2-ethyl-N-phenylimidazoline.

30 Preferably, 2-methylimidazole is used.

Generally, the accelerator is introduced into the sizing composition in an amount of 0.1 to 5 parts,  
35 preferably 0.5 to 3 parts and better still 0.5 to 2 parts, by weight of dry matter per 100 parts by weight of dry matter of epoxy resin/hardener.

The sizing composition may furthermore include the following additives, per 100 parts by weight of dry matter of resin/hardener:

- 0 to 2 parts, preferably around 0.5 parts, of a coupling agent such as a silane;
- 0 to 20 parts, preferably 6 to 15 parts, of an oil.

The well-known role of the aforementioned additives will be briefly recalled here:

- the water has a lubricating role and makes it possible to adjust the viscosity to the spraying conditions, to cool the fibres and limit pregelling effects;
- the coupling agent ensures bonding between the mineral fibre and the cured binder. It helps to increase the mechanical properties and contributes to improving the ageing resistance. The silane is generally an amino silane, preferably  $\gamma$ -aminopropyltriethoxysilane; and
- the oil lubricates the fibres, helps to reduce dust liable to be generated when handling the finished products (for example insulating sheets) and improves the feel. It is generally inert with respect to the other constituents and can be emulsified in water. Usually, it is an oil consisting of hydrocarbons extracted from petroleum.

The subject of the invention is also a process for manufacturing a thermal and/or acoustic insulation product, based on mineral wool provided with an epoxy binder, exhibiting better mechanical resistance after ageing, especially in a wet environment, in which process:

- a) mineral fibres are formed from a molten mineral composition;
- b) a sizing composition, comprising an epoxy resin of the glycidyl ether type, an amine hardener and

an accelerator chosen from imidazoles, imidazolines and mixtures thereof, is sprayed onto the fibres obtained at a);

c) the fibres are collected in the form of a  
5 sheet; and

d) the sheet is subjected to a heat treatment at a temperature below about 260°C, preferably around 220 to 240°C.

10 In general, it is necessary for the sizing composition to have a pot life compatible with the spraying conditions and for it not to cure before sheet formation. This means, in other words, that there must be as little pregelling of the size as possible.

15 Given that the rate of reaction between the amine functional groups of the hardener and the epoxide functional groups increases very rapidly in the presence of the accelerator, preparation of the size by  
20 mixing, even extemporaneously, the epoxy resin, the amine hardener, the accelerator and optionally, the additives prior to spraying is to be avoided in order to prevent any risk of the spray ring becoming blocked.

25 It is preferred to spray the size onto the fibres according to the following two methods of implementation.

In a first method of implementation, the accelerator is  
30 mixed with the other constituents of the size, preferably upstream of the spray ring and as late as possible, and then the size is applied in the usual manner to the mineral wool. This method of  
implementation is advantageous when the rate of  
35 reaction between the epoxy resin and the amine hardener is low enough and does not cause premature gelling that may lead to total or partial blockage of the spray means.

According to a first variant, the accelerator is introduced into the mixture of the other constituents of the size, which constituents may be introduced  
5 separately or may have been mixed beforehand (forming a premix). It is preferred to introduce the accelerator into a premix containing all of the other constituents of the size.

---

10 According to a second variant, a first mixture, consisting of the accelerator and the amine hardener, is produced and a second mixture, consisting of the epoxy resin and the other constituents of the size, is produced, and then the said first and second mixtures  
15 are introduced before the spray ring.

In a second preferred method of implementation, valid even when the reactivity of the size is low, the accelerator is applied separately from the spraying of  
20 the other constituents of the size onto the fibres. For example, the accelerator in aqueous phase can be sprayed near the ring for spraying the other constituents of the size, especially by superposing two spray rings in the path of the mineral wool in the  
25 direction of the receiving member, one ring (preferably the first in the direction of advance of the wool) spraying the accelerator and the second one spraying the other constituents of the size.

30 The insulation products obtained according to one or other of the methods of implementation, which also constitute a subject of the invention, contain 0.5 to 15%, preferably 1 to 12%, by weight of cured binder relative to the total weight of mineral fibres. In its  
35 crosslinked form, the binder is solid, infusible and insoluble in water.

The products obtained are white in colour, if no

colorant has been added.

The insulation products obtained may have the appearance of a sheet or a veil. They may be in the form of a panel of variable stiffness, a shell, or a roll (of felt or veil). Where appropriate, at least one of their faces is coated with a layer or film for protecting the mineral wool, for example a veil of mineral fibres, preferably glass fibres, or a sheet of kraft paper. Particularly preferably, the veil of fibres has a weight of between 10 and 300 g/m<sup>2</sup> and contains at least 1%, preferably at least 2% and advantageously at least 4%, by weight of cured binder obtained from the size according to the invention.

The products obtained within the context of the present invention are especially intended to form thermal and/or acoustic insulation products, in particular for buildings and for applications requiring high resistance to high temperatures (industrial shells and domestic ovens. They may also serve as substrates for soilless cultivation.

The following non-limiting examples illustrate the invention.

#### **EXAMPLE**

Glass wool was manufactured using the internal centrifugal technique in which the molten glass composition was converted into fibres by means of a tool called a spinner, comprising a basket forming a chamber for receiving the molten composition and a peripheral band pierced by a multitude of holes. The spinner was rotated about its axis of symmetry, placed vertically, the composition was ejected through the holes under the effect of the centrifugal force, and the material escaping from the holes was attenuated

into fibres with the assistance of an attenuation gas stream.

5 In the conventional manner, a size spray ring was placed beneath the fibrizing spinner so as to spread the sizing composition uniformly over the glass wool as it was being formed.

10 The mineral wool thus sized was collected on a belt conveyor equipped with internal suction boxes that held the mineral wool, in the form of a felt or sheet, on the surface of the conveyor. The conveyor then ran through an oven maintained at 220°C in which the resin of the size was cured to form a binder.

15 The composition of the size was the following (in parts by weight of dry matter):

- epoxy resin of the glycidyl ether type:  
Epi-Rez<sup>®</sup> 3510-w-60 (from Resolution): 85 parts
- 20 - hardener: tetraethylenepentamine (TEPA) 15 parts
- accelerator: 2-methylimidazole 1 part
- coupling agent: Silquest<sup>®</sup> A1100  
(from Crompton) 0.5 parts
- oil: Mulrex<sup>®</sup> 88 (from Mobil) 9.5 parts

25 The size composition was sprayed under the following conditions: a first mixture, comprising the resin, the coupling agent and the oil, and a second mixture, comprising the hardener and the accelerator, were  
30 produced. These two mixtures were fed separately into the spray ring and combined just before their introduction into the said ring. The spray rate was set so as to deposit around 5% by weight of dry matter relative to the weight of glass wool.

35 Two control tests were carried out with a size not containing the accelerator, the first being treated in an oven at 220°C (Control 1) and the second at a

temperature of 260°C (Control 2).

Another control test was also carried out with a size  
containing 2,4,6-tri(dimethylaminomethyl)phenol as  
5 accelerator (Control 3).

The tensile strength after manufacture ( $TS_{\text{man}}$ ) and the  
tensile strength after accelerated ageing in an  
autoclave at a temperature of 105°C and 100% relative  
10 humidity for 15 minutes ( $TS_{15}$ ) or 45 minutes ( $TS_{45}$ ) were  
measured on the product obtained.

The tensile strength TS was measured according to the  
ASTM C 686-71T standard on a specimen cut from the  
15 insulation product by stamping. The specimen had the  
shape of a torus 122 mm in length, 46 mm in width, a  
radius of curvature of the cut at the outer edge equal  
to 38 mm and a radius of curvature of the cut at the  
inner edge equal to 12.5 mm.

20 The specimen was placed between two cylindrical  
mandrels of a test machine, one of which was mobile and  
moved at a constant speed. The breaking force F (in  
grams force) of the specimen was measured and the  
25 tensile strength TS defined by the ratio of the  
breaking force F to the mass of the specimen was  
calculated.

The results are given in Table 1, which indicates, for  
30 each test, the percentage loss of tensile strength  
relative to the initial state after manufacture and the  
percentage improvement over the control containing no  
accelerator (the value in brackets).

35 The thickness recovery was measured on the product  
obtained, allowing the dimensional behaviour to be  
assessed. The procedure was as follows: the product was  
compressed with a degree of compression (defined as the



ratio of the nominal thickness to the thickness under compression) of 6/1 for 1, 12 and 30 days. The thickness recovery corresponds to the ratio of the thickness after compression to the nominal thickness (expressed in per cent). The results are given in Table 1.

Table 1

	TS <sub>man</sub>	TS <sub>15</sub>	Loss	TS <sub>45</sub>	Loss	Thickness		
		(gForce/g)	(%)	(gForce/g)	(%)	recovery (%)		
						1 d	12 d	30 d
<b>Example</b>	302 (-4.4%)	204 (+25.9%)	32.5	167 (+51.8%)	44.7	140	138	137
<b>Control 1</b>	316	162	48.7	110	65.2	137	136	136
<b>Control 2</b>	300	159	47.0	120	60.0	140	137	136
<b>Control 3</b>	301]	147	51.1	110]	63.5	141	139	138
<b>Control 4</b>	327	253	22.2	208	36.0	143	137	137

The results in Table 1 show that the product according to the invention (Example) has a better tensile strength than the equivalent product containing no accelerator (Control 1) and the percentage loss after ageing is less, whether after 15 minutes or 45 minutes of autoclave treatment.

Compared with the product containing no accelerator, the improvement in tensile strength of the highly aged products is equal to 51.8%, which represents a very substantial improvement.

It should be noted that the presence of the catalyst does not degrade the properties of the products according to the invention, whether as regards tensile

strength after manufacture ( $TS_{\text{man}}$ ) or thickness recovery.

5 An improvement in tensile strength is not obtained with the conventional accelerator of Control 3. Nor does the higher curing temperature (of Control 2) make it possible to achieve a better tensile strength after ageing. For comparison, Table 1 indicates the tensile strength and thickness recovery values of a standard  
10 product (Control 4) treated with a size incorporating a conventional phenol-formaldehyde resin in an oven at 260°C.

The size had the following composition (in parts by weight):  
15

- phenol-formaldehyde resin	55 parts
- urea	45 parts
- coupling agent (Silquest® A 1100)	0.5 parts
- oil (Mulrex® 88)	9 parts
20 - ammonium sulphate	3 parts
- aqueous ammonia (20% solution)	6 parts

The phenolic resin was of the type described in EP-A-0 148 050.  
25

The product according to the invention does not have the level of performance of that containing a phenolic resin; nevertheless, it does constitute a good compromise as it reconciles good ageing resistance,  
30 especially in a wet environment, with a very low level of emissions of undesirable gases (which is not the case with phenolic resins, which release formaldehyde) and a lower energy cost, thanks to the use of ovens operating at lower temperature.

35

**CLAIMS**

1. Sizing composition for insulation products based on mineral wool, especially glass or rock wool, comprising an epoxy resin of the glycidyl ether type and an amine hardener, characterized in that it furthermore includes an accelerator chosen from imidazoles, imidazolines and mixtures thereof.

10 2. Composition according to Claim 2, characterized in that the accelerator is imidazole, 1-methylimidazole, 2-methylimidazole, 2-phenylimidazole, 2-ethyl-4-methylimidazole, 4,4'-methylenebis(2-ethyl-5-methylimidazole) and 2-ethyl-N-phenylimidazoline.

15 3. Composition according to Claim 1 or 2, characterized in that the epoxy resin is obtained by the reaction of epichlorohydrin with an alcohol, preferably a polyol.

20 4. Composition according to one of Claims 1 to 3, characterized in that the resin has an EEW (Epoxy Equivalent Weight) of between 150 and 2000, preferably between 160 and 700 and better still at most equal to 25 300.

5. Composition according to one of Claims 1 to 4, characterized in that the epoxy resin has a water dilutability, at 20°C, of at least 500%, preferably 30 1000%.

6. Composition according to one of Claims 1 to 5, characterized in that the hardener is chosen from aliphatic polyamides, such as diethylenetriamine (DETA), triethylenetetramine (TETA), tetraethylene- 35 pentamine (TEPA) and polyglycoldiamines, cycloaliphatic polyamines, such as 1,3-bis(aminomethyl)cyclohexane, 4,4-diaminocyclohexylmethane, methylenediamine and

2,4-diaminocyclohexanol, and aromatic polyamines, such as m-phenylenediamine, m-xylylenediamine, diethyltoluenediamine, diaminodiphenylsulphone and dicyandiamine.

5

7. Composition according to one of Claims 1 to 6, characterized in that it contains the accelerator in an amount of 0.1 to 5 parts by weight of dry matter per 100 parts by weight of dry matter of epoxy resin/hardener.

---

10

8. Composition according to one of Claims 1 to 7, characterized in that the hardener has an amine equivalent weight/H ratio of 20 to 300.

15

9. Composition according to one of Claims 1 to 8, characterized in that it furthermore includes the following additives, per 100 parts by weight of dry matter of resin/hardener:

20

- 0 to 2 parts, preferably around 0.5 part, of a coupling agent such as a silane;
- 0 to 20 parts, preferably 6 to 15 parts, of an oil.

25

10. Process for manufacturing a thermal and/or acoustic insulation product, based on mineral wool, in which:

a) mineral fibres are formed from a molten mineral composition;

30

b) a sizing composition according to one of Claims 1 to 10 is sprayed onto the fibres obtained at a);

c) the fibres are collected in the form of a sheet; and

35

d) the sheet is subjected to a heat treatment at a temperature below about 260°C, preferably around 220 to 240°C.

11. Process according to Claim 10, characterized in

that the accelerator is mixed with the other constituents of the size before being sprayed onto the fibres.

- 5 12. Process according to Claim 10, characterized in that the accelerator is applied separately from the spraying of the other constituents of the size onto the fibres.

---

10 13. Thermal and/or acoustic insulation product based on mineral wool, especially glass or rock wool, provided with a sizing composition according to one of Claims 1 to 9.

15 14. Product according to Claim 13, characterized in that the total weight of cured binder represents from 0.5 to 15%, preferably 1 to 12% of the total weight of mineral fibres.

20 15. Product according to Claim 13 or 14, characterized in that it furthermore includes a veil of mineral fibres, especially glass fibres, having a weight of between 10 and 300 g/m<sup>2</sup>, placed on at least one of the external faces of the said product and in that the said  
25 veil comprises at least 1% by weight of cured binder obtained from the sizing composition according to one of Claims 1 to 9.

16. Use of the sizing composition according to one of  
30 Claims 1 to 9 for improving the mechanical strength after ageing, especially in a wet environment, of insulation products based on mineral wool.

17. Use according to Claim 15, characterized in that  
35 the wool is glass wool or rock wool.

**PATENT****UTILITY CERTIFICATE**

Intellectual Property Code - Book VI



N° 11235\*02

**PATENTS DEPARTMENT**

26 bis, rue de Saint Pétersbourg  
75800 Paris Cedex 08  
Telephone: 01 53 04 53 04 Fax: 01 42 93 59 30

**DESIGNATION OF THE INVENTOR(S) Page No. . 1 . / . 1**  
(if the applicant is not the inventor or the sole inventor)

This form is to be filled in legibly in black ink

DB 113 W / 260899

<b>Your file references</b> (optional)		PaC32003096 FR	
<b>NATIONAL REGISTRATION NO.</b>		03/12,973	
<b>TITLE OF THE INVENTION (200 characters or spaces maximum)</b>  SIZING COMPOSITION FOR AN INSULATION PRODUCT BASED ON MINERAL WOOL, AND RESULTING PRODUCTS.			
<b>THE APPLICANT(S):</b>  SAINT-GOBAIN ISOVER 18 Avenue d'Alsace F-92400 COURBEVOIE FRANCE			
<b>DESIGNATE(S) AS INVENTOR(S):</b> (Indicate top right "Page 1/1". If there are more than 3 inventors, use an identical form and number each page, indicating the total number of pages.)			
Name		ESPIARD	
Forenames		Philippe	
Address	Street	2 rue des Primevères	
	Postcode and town	60270	GOUVIEUX
Employer company (optional)			
Name			
Forenames			
Address	Street		
	Postcode and town		
Employer company (optional)			
Name			
Forenames			
Address	Street		
	Postcode and town		
Employer company (optional)			
<b>DATE AND SIGNATURE(S) OF THE APPLICANT(S) OR OF THE REPRESENTATIVE (Name and capacity of the signatory)</b> 5 November 2003 SAINT-GOBAIN RECHERCHE Power of Attorney No. 422-5/S.006 Patricia CHOSSON		[signature]	